

(\*掲載記事題目及び掲載頁は変更になる場合があります。)

## Fundamentals of High Temperature Processes

### Aluminum deoxidation equilibrium in liquid Fe-36%Ni alloy

S.-B. LEE *et al.*

For thermodynamic prediction, the deoxidation equilibrium of aluminum in Fe-36%Ni alloy was investigated by employing a cold crucible under an Ar gas atmosphere at 1 773 K. The interaction parameters between aluminum and oxygen by taking liquid Fe-36%Ni alloy as the basis (*i.e.*, solvent) are evaluated as follows:

$$e_{\text{O}}^{\text{Al}} = -3.8, r_{\text{O}}^{\text{Al}} = 0.9, e_{\text{Al}}^{\text{O}} = -6.4, \\ r_{\text{Al}}^{\text{O}} = 700, r_{\text{Al}}^{\text{Al}_2\text{O}_3} = 3.1, r_{\text{O}}^{\text{Al}_2\text{O}_3} = 833$$

within the composition range of [Al] < 1 mass%.

The equilibrium constant for reaction  $2\text{Al}_{(\text{in Fe-36\%Ni})} + 3\text{O}_{(\text{in Fe-36\%Ni})} = \text{Al}_2\text{O}_{3(\text{s})}$  was obtained in the temperature range of 1 773 to 1 973 K by using data from the present study and from previous works reported:

$$\log K_{AO} = 0.58 - 24 460/T$$

The deoxidation equilibrium of aluminum in Fe-36%Ni can thus be thermodynamically described in the range of [Al] < 1 mass% using both the first and second order interaction parameters as well as the equilibrium constant determined in this study.

(*cf. ISIJ Int.*, 42 (2002), 679)

### Behavior of magnesium in the desulfurization process of molten iron with magnesium vapor produced *in-situ* by aluminothermic reduction of magnesium oxide

J. YANG *et al.*

The behavior of magnesium in the desulfurization process of molten iron with magnesium vapor produced *in-situ* by the aluminothermic reduction of magnesium oxide has been investigated.

The magnesium concentration first increased rapidly, reaching the maximum, and then decreased gradually to a very low level. The magnesium concentration of the molten iron was mainly that of the dissolved magnesium and the following decrease in the magnesium concentration was due to the evaporation from the melt surface and the mass transfer of the dissolved magnesium to the bubble surface. Under the present experimental conditions, the magnesium concentration increased with increasing temperature, pellet mass, carrier gas flow rate and decreasing initial sulfur concentration.

Decreasing the pellet mass and increasing initial sulfur concentration made the desulfurization efficiency higher and decreased the amounts of magnesium dissolving into the melt and leaving the melt. The equilibrium relation between [ppmMg] and [ppmS] did not conflict with the present experimental results at temperatures from 1 553 to 1 673 K.

A mathematical model for analyzing the behavior of magnesium in the present desulfurization process has been developed. The calculated magnesium and sulfur concentrations are well consistent with the experimental results. The calculated results demonstrate that the existence of the peak of magnesium concentration is reasonable. The present mathemat-

ical model can also explain the effects of pellet mass and initial sulfur concentration on the behavior of magnesium injected into the melt.

(*cf. ISIJ Int.*, 42 (2002), 685)

## Ironmaking

### Sloshing of melts in a bath smelting process having an elliptic cross section

J.-L. LIOW

Recently, the use of the elliptic cross section cylinder for bath smelting operations was adopted by the AusIron process. The high gas flow rates used have been found to generate wave motion in the bath that can enhance refractory wear. The standing wave modes were found for the bath. Two distinct sets of eigenvalues were obtained, one in the major axis and the other in the minor axis. The two sets converged when the ellipticity of the cylinder is zero, which is the shape of a circle. The calculated wave frequency was found to agree well with experimental data. A complete set of eigenvalues have been calculated for elliptic cylinders and fitted to Chebyshev polynomials, enabling quick estimation of the standing wave frequencies. The study showed that the ellipticity of the vessel for the AusIron process needs to be carefully chosen as the standing wave modes that can be generated may result in beat frequencies that can interact with the natural frequencies of the vessel support and auxilliary equipment.

(*cf. ISIJ Int.*, 42 (2002), 694)

## Casting and Solidification

### Microstructure simulation of aluminum alloy using parallel computing technique

W. FENG *et al.*

The formation and evolution of the microstructure of casting are important research areas in the field of material science and engineering. The solidified microstructure of aluminum alloy was simulated by combining the CA (Cellular Automaton) model with macro heat transfer. A modified CA (MCA) model, which uses a more similar shape to the actual dendrite to describe the growth grain, was proposed and studied. Because of the huge computational capacity to simulate the microstructure of casting, a relevant parallel computing technique based on the serial arithmetic was developed, which can greatly improve the computing scale and efficiency and can also ensure the computing accuracy as well. The simulation results are compared with the experimental results and agreed quite well.

(*cf. ISIJ Int.*, 42 (2002), 702)

### Compression test to reveal surface crack sensitivity between 700 and 1 100°C of Nb-bearing and high Ni continuous casting slabs

S.S. XIE *et al.*

In this study, the surface crack sensitivities in samples of a Nb-bearing steel and a high Ni grade steel from continuous casting slabs have been examined by simple compression tests at various temperatures between 700–1 100°C using a metallography

method to evaluate the severity of surface cracks, and corresponding microstructure in the two grades of steel has been investigated. The results show that most specimen have cracks on the hoop surface after 50% compression in height in the temperature range of interest, and the critical hoop strain obtained from the metallography examination gives a clear cracking tendency for the two grades of steel. Microstructure observation revealed that the static precipitation of TiNb(CN) before deformation and thin ferrite film along grain boundaries are important for controlling surface crack sensitivity for the Nb-bearing steel, while coarse grains with flat boundaries, and grain-boundary precipitation of Cu<sub>2</sub>S and flake-like Ti(CN) at lower temperature, is responsible for the high crack sensitivity in high Ni steel between 700–1 100°C, which implies Cu, S, Ti and N content should be kept as low as possible in this grade of steel, and surface temperatures of continuous casting slabs at the straightening point should be above 970°C for Nb-bearing steel while 980°C for high Ni steel to avoid transverse cracking.

(*cf. ISIJ Int.*, 42 (2002), 708)

### Collision and coalescence of alumina particles in the vertical bending continuous caster

H. LEE *et al.*

The three-dimensional fluid flow in a vertical bending continuous caster was numerically studied. Three dimensionless collision numbers were introduced to analyze the inclusion collision mechanism. The analysis showed that turbulent collisions were the major factor causing inclusions to collide with each other in the continuous caster. Stokes collisions had a minor effect and Brownian collisions were negligible. A mathematical model was then developed to study the inclusion collisions in the continuous caster. The mathematical model considered the inclusion mass transfer and expressed the radius and population of new inclusions after coalescence relative to the mass and population conservation. Since the motion of cluster-shaped inclusions differs from that of spherical inclusions, the inclusion physical parameters were modified. The results showed that the inclusions congregated approximately one fourth of the face width from the slab edge so that the characteristic radius distribution of the inclusions had a 'W' shape, while the inclusion concentration and number density had an inverse 'W' shape in the longitudinal direction. More inclusions were trapped near the inner arc and they had larger characteristic radii than those near the outer arc. The concentration and inclusion number density decreased with the distance from the free surface, but the inclusion radius increased.

(*cf. ISIJ Int.*, 42 (2002), 717)

### Forming Processing and Thermomechanical Treatment

#### Prediction of the surface profile and area of the exit cross section of workpiece in round-oval-round pass sequence

Y. LEE

In this paper, the model<sup>9)</sup> that predicts the surface

profile and area of exit cross section of workpiece in oval-round (or round-oval) pass rolling sequence has been improved. Afterward, the generality and robustness of the model was studied to assess the potential that finite element method generally used for predicting it might be replaced by the model. Since only the shape of the inlet cross-section of workpiece and geometry of the roll groove are considered in the model, the problem of obtaining the final rolled shape is greatly simplified and subsequently the computational time required for whole rolling process is a few seconds.

Extensive hot bar rolling experiments at different temperatures (800–1100°C) was carried out to investigate the effect of the change of rolling conditions and material parameters, such as the ratio of the specimen diameter to roll diameter, roll gap (*i.e.*, pass height), roll groove design, steel grades and temperature of material on the model. This model has then been applied to a rod mill to extend its application coverage.

It was shown that the predicted surface profile and area of exit cross section are in good agreement with those experimentally measured for the variation of rolling conditions and material parameters. It was found that if we are interested in the capability for predicting the surface profile and area of exit cross section of workpiece for the entire rod (or bar) rolling line within a very short time, the proposed model might be an alternative which can replace the three-dimensional finite element method usually used in the analysis of rod (or bar) rolling analysis.

(*cf.* *ISIJ Int.*, **42** (2002), 726)

### Effect of the number of work-roll surface division on prediction of contact length in coupled analysis of roll and strip deformation during sheet rolling

*H. FURUMOTO et al.*

In order to perform accurate three-dimensional rolling analysis of sheet deformation, it is required to predict the contact length accurately in consideration of the surface waviness due to the flattening deformation of work roll surface. Flattening deformation analysis based on theory of elasticity and three-dimensional elastic FEM have been developed, and their accuracy in predicting flattening deformation and contact length are validated in this report. As the flattening deformation of the work roll surface changes sharply at the boundary of contact area, the contact length is expected to change according to the number of work roll surface division, especially in circumferential direction, for calculation. Then, the influences of the number of division on roll profile and contact length used for numerical analysis are investigated. The following results are obtained; 1) The differences between the results obtained by three-dimensional elastic FEM and formula for roll flattening of Nakajima and Matsumoto is not significant. 2) When the number of division of work roll surface is increased, the end point of contact region moves toward the downstream side, therefore, the contact length becomes longer and it is necessary to divide the work roll surface into enough much elements. 3) As long as enough much elements are used for the calculation, solutions, such as rolling

pressure distribution or thickness distribution of rolled strip, obtained by three-dimensional analysis reveal little difference from those obtained using formula for roll flattening given by Hitchcock.

(*cf.* *ISIJ Int.*, **42** (2002), 736)

## Transformations and Microstructures

### Ultrafine grain structure through dynamic recrystallization for type 304 stainless steel

*I. SALVATORI et al.*

Ultrafine grain structure in the type 304 austenitic stainless steel are pursued through dynamic recrystallization. The recrystallization behaviors are studied at various combinations of deformation temperatures and strain rates accompanying the higher strain under a plain strain compression. The effects of the strain, the strain rate and the deformation temperature are investigated, and the relationship between the deformation conditions and the dynamic recrystallized grain size is analyzed. The critical strain needed for the initiation of recrystallization increases with the  $Z-H$  parameter. Empirical equations concerning the critical strain and the dynamic recrystallized grain size are discussed, and processing parameter maps are proposed for the complete dynamic recrystallization.

(*cf.* *ISIJ Int.*, **42** (2002), 744)

### The deformation microstructure and recrystallization behavior of warm rolled steels

*D. LIU et al.*

The deformation microstructure of various warm (ferritic) rolled steels was characterized and its influence upon the subsequent annealing behavior determined. The materials investigated included three interstitial-free (IF) steels (stabilized with either titanium or niobium), an extra low carbon (ELC) steel, and four experimental low carbon chromium steels with varying levels of boron, nitrogen and phosphorus. Single pass rolling experiments were conducted in a pilot mill at temperatures between 440 and 850°C and the as-rolled microstructures were examined using optical microscopy. Particular attention was paid to the nature and intensity of the in-grain shear bands produced. Partial annealing was conducted to examine the nucleation of recrystallization in the deformed microstructure. Shear bands of moderate intensity were usually formed in the IF steels, which tended to be insensitive to rolling temperature. For the ELC steel, intense shear bands were formed at low rolling temperatures, but at higher temperatures this intensity was found to be drastically reduced. The development of shear bands at the higher rolling temperatures was significantly enhanced by alloying with chromium. The differences in shear band frequency and intensity are explained in terms of the dynamic strain aging behaviors of the various materials. Recrystallized grains were found to nucleate preferentially on the shear bands during annealing, regardless of their morphology or intensity.

(*cf.* *ISIJ Int.*, **42** (2002), 751)

### Modelling simultaneous alloy carbide sequence in power plant steels

*N. FUJITA et al.*

A method has recently been developed to estimate the speed with which precipitation reactions occur in power plant steels. It is based on Avrami theory but with an adaptation that allows the treatment of simultaneous reactions. In the present work, a number of approximations and inconsistencies in the theory have been eliminated and this kinetic theory for simultaneous reactions has been modified with the treatments of both diffusion-controlled growth and capillarity effect in multicomponent systems. The modified model can predict not only volume fraction changes of each carbide but also particle sizes. New experimental results on alloy carbide in 3Cr1.5Mo and 2 $\frac{1}{4}$ Cr1Mo steels are reported and shown to be comparable to the modified theory.

(*cf.* *ISIJ Int.*, **42** (2002), 760)

### Development of cold rolled texture and microstructure in a hot band Fe-3%Si steel

*S. CICALÈ et al.*

Hot band Fe-3%Si steel (CRGO or cold rolled grain oriented) was cold rolled with different reductions. The main objective of this study was an overall understanding of deformation texture and microstructure development. Hot band CRGO had a strong  $\alpha$ -fiber (RD//{110}) texture. Cold reduction strengthened the  $\alpha$  and  $\gamma$  (ND//{111}) fibers, but weakened  $\theta$  (ND//{100}). All Taylor type deformation texture models were reasonably successful in predicting these bulk texture developments, and the Lamel model seems to be the 'best-fit' model, both in terms of a 'deviation' parameter (indicating differences between experimental and simulated values of idealized texture components) and a 'trend' parameter (indicating the relative change(s) in texture components with strain). The striking feature of the microstructure was the 'selective' appearance of grain interior strain localizations. These appeared at approximately 37° with the rolling direction (RD). Though 37° bands appeared only in orientations with high Taylor factor ( $M$ ), the absolute value of the Taylor factor alone, was not enough for the appearance of such bands. Negative textural softening or ( $dM/d\varepsilon$ ) values, on the other hand, were always associated with the appearance of 37° bands, justifying or explaining their formation on the basis of a macroscopic plastic instability theory.

(*cf.* *ISIJ Int.*, **42** (2002), 770)

## Mechanical Properties

### Effect of heat treatment on precipitation kinetics in high-Cr ferritic steels

*K. YAMADA et al.*

Precipitation strengthening is important to improve creep strength of heat resisting steels at elevated temperatures. Especially, in the high-Cr ferritic steels recently developed for Ultra Super Critical Power Plants, precipitation behavior is complicated and should be clarified because the correlation between various strengthening factors are still not well